

**** MARSHALL'S COVE BRAND MARINE PAINT****

TRADITIONAL DURABLE MARINE FINISH



TECHNICAL DATA SHEET FOR COATINGS AND RELATED MATERIALS

Colors

Whites and Tints

PRODUCT TYPE

Pigmented Gloss Alkyd Enamel

DESCRIPTION

MARSHALL'S COVE BRAND MARINE PAINT (MCBMP) is a no-frills, durable marine enamel designed for top coats on wood or steel. Ask for MARSHALL'S COVE BRAND MARINE PAINT at your local chandlery.

PHYSICAL CHARACTERISTICS

Viscosity: 70-80 k.u.

Weight Solids: 50-60% depending upon color* **Volume Solids:** 42-45% depending upon color* Weight Per Gallon: 7.60-9.50 lbs. per gallon V.O.C.: 439 grams per liter

107° F

Flash Point:

Practical Coverage: 300-500 sq. ft. per gal. depending on application.

Dry To Touch: 1 hour Tack Free: 6-8 hours Time To Recoat: Overnight Dry Hard: 8 hours

Color Range: Whites and Tints 1 or 5 gallon containers Packaging:

Batch: Stock

SURFACE PREPARATION

Surface must be clean, dry, properly prepared and free of dirt, grease, or loose chipping paint and particles. Glossy surfaces must be de-glossed with sandpaper or similar process before finishing. New or bare surfaces should be primed with a suitable primer before applying finish coat.

APPLICATION

Brush, roller, or airless or conventional spray. Note: This material needs little or no thinning for brushing and rolling. The consistency has been formulated to provide best results from full-body application.

THINNING

Thin if necessary with turpentine, mineral spirits or synthetic thinner.

Tools and equipment may be cleaned with mineral spirits or synthetic thinner.

**** MARSHALL'S COVE BRAND MARINE PAINT ****

PETERMARSHALL, PROPRIETOR | 425.260.3509 | PETER@MARSHALLSCOVEMARINEPAINT.COM | WWW.MARSHALLSCOVEMARINEPAINT.COM | PO BOX836 | BELLEVUE, WA 98009

LIMITED WARRANTY. To the best of our knowledge, the technical data presented above is true and accurate at the date of issuance and subject to change withour prior notice. Marshall's Cove Brand Marine Paint (MCBMP) guarantees its products to conform to its standards of quality control. Liability is limited to replacement of product. No other warranty or guarantee of any kind is made by MCBMP, implied or otherwise.

^{*} Contact MCBMP yfor specific weight solids and volume solids % on individual colors. 307° to 389°